

GREENHOUSE COVER

TYPE SPECIAL FAETURE/ VP - 1B

FILM USAGE
WIDTH
THICKNESS
LENGTH

GREENHOUSE COVER
UP TO 12.2 METERS
150 MICRON OR 200 MICRON
AS REQUIRED

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	23
	TD		MPa	22
Elongation at break	MD		%	620
	TD		%	750
Tear resistance	MD	ASTM D-1922	Gr./mm	8500
	TD		Gr./mm	10000
Falling dart drop impact		ASTM D-1709	Gram	800
Light transmission in PAR	%	ASTM D-1003		89
Diffused light tr. in PAR	%			55
UV – Transm. 300 - 380 nm.	%			0
Thermicity	%	Internal "FT-IR"		80
			Typical values	



Vanphuc Trading & Production Co.,LTD

Vietnam | Tel +84 2213989826/8 | Fax +84 221989826

Email: vanphucplastic@gmail.com | Web site: www.vanphucplastic.com